

OPTICAL RECORDING MEDIUM AND METHOD

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The present invention relates to an optical recording medium and method, which records information by irradiating a laser beam to a recording layer so as to form a recording mark, and in particular, to a technology of forming a plurality of recording marks having different state so as to record a data at a multi-level.

2. Description of the Related Art

10 In a conventional optical recording medium, a method has been employed such that a data is recorded by changing a length of read signal (i.e., a length of reflection signal modulation section). On the contrary, the following method has been frequently studied, more specifically, a plurality of data is recorded to each signal having the same length by changing a depth of the read signal (i.e., a modulation degree of reflection signal) at multiple stages.

15 According to the above optical recording method, as compared with the case where a binary data is merely recorded by the presence of pit, a plurality of data is recorded in a depth direction, so that a signal quantity allocated to a constant length can be increased; therefore, it is possible to improve a track recording density. In general, it is well known to change a power of laser beam at multiple stages, as the method of a depth of read signal at multiple stages. Recently, holograph

20

25

has been used as the recording medium, and a recording medium having a multiple recording layer has been proposed.

In this case, it is called as multi-level recording to record each data so that a modulation degree of reflection signal is variable at multiple stages.

In the above multi-level recording, a laser beam is irradiated at multiple-stage power in recording; for this reason, in particular, when the power of laser beam gradually becomes large, a problem has arisen such that a signal quality is worsened in reading. Although the above cause has not been proved, the present inventors presume the cause as follows; more specifically, the laser power increases, and thereby, a recording mark area increases.

For example, in order to achieve a high density of the recording information of recording medium, in the case where multi-level recording is carried out in a manner of making small a recording mark, and changing a laser power at multiple stages, a signal quality has remarkably worsened in the recording mark recorded by large laser power.

Namely, if the multi-level recording method is employed using power change, a distance (interval) between the recording marks is made wide, and data detection must be securely made to some degree even if the signal quality has worsened.

Moreover, the conventional concept of achieving the multi-level recording by stepwise changing the laser power is based on the following premise that the recording mark length is at least larger than a radius of focused beam (beam waist)

in recording. In general, a diameter of the focused beam is expressed as $K\lambda/NA$ (K : constant, λ : laser wavelength, NA : numerical aperture of lens. For example, in a pickup used for a CD, the laser wavelength λ is 780 nm, the numerical aperture NA is 0.50, and the diameter of focused beam is about $0.8\mu\text{m}$. Thus, when the recording mark length is made small up to the vicinity of about $0.8\mu\text{m}$, the above problem of signal deterioration has remarkably arisen. In fact, it is very difficult to achieve five-stage or more multi-level recording by the method of changing a laser power.

On the contrary, although is unknown when this application has been filed, an optical recording method has been disclosed in Japanese Patent application No. 2000-187568 filed by the same applicant as this application. More specifically, according to the above optical recording method, in place of the power of laser beam, an irradiation time to a predetermined virtual recording cell area is changed at multiple stages. By doing so, a recording mark (low optical reflectance area) having different size is formed in the entire virtual recording cell and brings different optical reflectance to the virtual recording cell; therefore, at least five-stage multi-level recording is possible.

The above optical recording method is a concept quite different from the conventional laser beam irradiation, and a recording mark may be formed by a short-time irradiation. Therefore, the case is sufficiently considered such that a recording mark smaller than a beam spot diameter is formed. In

other words, multi-stage (five stages or more) and high density multi-level recording can be realized by effectively using an area in which the recording mark has been conventionally considered as being incomplete.

5

SUMMARY OF THE INVENTION

The present invention has been made in order to further study the above technology. Accordingly, an object of the present invention is to provide an optical recording medium, which can achieve multi-stage (multi-level) and high read-accuracy multi-level recording by setting a power of laser beam to a predetermined range.

The present inventors have earnestly studied optical recording medium and method; as a result, they have confirmed that it is possible to carry out multi-stage and stable high density multi-level recording.

(1) In order to achieve the above object, according to one aspect, the present invention provides an optical recording medium, including a reflective layer and a recording layer, and constructed in a manner that a recording mark is formed on the recording layer by irradiating a laser beam so as to record information,

the recording layer being continuously formed in a relative moving direction to the laser beam with plural virtual recording cells, each of which has an arbitrary unit length and a unit width perpendicular to the unit length in the relative moving direction,

five stages or more irradiation times being set with respect to the virtual recording cell so that the irradiation time becomes long successively from the first to final stages,

a power average value of laser beam in a specific irradiation time of the plural-stage irradiation times being set so as to become larger than a power average value of another irradiation time longer than the specific irradiation time, and

recording marks being formed in the virtual recording cell and giving five stages or more different optical reflectance to the virtual recording cell when the laser beam is irradiated to the virtual recording cell.

(2) Further, the present invention provides the optical recording medium, wherein in the plural irradiation times from the first stage to at least second stage, a power average value of laser beam of each stage is set so as to become longer than a power average value of another irradiation time longer than the plural irradiation times.

(3) Further, the present invention provides the optical recording medium, wherein in at least first stage irradiation time, the power of laser beam is set larger than a reference power until the midway time point from the irradiation start timepoint, and is set to the reference power until the termination time from the midway time point, and

in another irradiation time longer than the irradiation time, the power of laser beam is set to the reference power until the termination time from the irradiation start time point.

(4) Further, the present invention provides the optical

recording medium, wherein in at least first stage irradiation time, the power of laser beam is set larger than a reference power until the termination time point from the irradiation start time point, and

5 in another irradiation time longer than the irradiation time, the power of laser beam is set to the reference power until the termination time from the irradiation start time point.

(5) Further, the present invention provides an optical recording medium, including a reflective layer and a recording layer, and constructed in a manner that a recording mark is formed on the recording layer by irradiating a laser beam so as to record information,

10 the recording layer being continuously formed in a relative moving direction to the laser beam with plural virtual recording cells, each of which has an arbitrary unit length and a unit width perpendicular to the unit length in the relative moving direction,

15 five stages or more irradiation times being set with respect to the virtual recording cell so that the irradiation time becomes long successively from the first to final stages,

20 a reference time shorter than the final stage irradiation being set,

the laser beam being irradiated in all range at a power larger than a reference power in an irradiation time shorter than the reference time of the plural stage irradiation times, and being irradiated at a power larger than a reference power in an irradiation time longer than the reference time until the

25

reference time elapsed from the irradiation start time point, and further, being irradiated at the reference power after the reference time elapsed,

when the laser beam irradiation time is short, the irradiation time at the reference power after the reference time elapsed decreasing so that a ratio of the irradiation time at the larger power increases, and thereby, a power average value of the laser beam becoming large so that recording mark having five stages or more different optical reflectance.

(6) Further, the present invention provides the optical recording medium, wherein the recording layer contains an organic dye.

(7) Moreover, in order to achieve the above object, according to another aspect, the present invention provides an optical recording method, which irradiates an laser beam to an optical recording medium including a reflective layer and a recording layer, and forms a recording mark is formed on the recording layer so as to record information, comprising the following stages of:

continuously forming plural virtual recording cells, each of which has an arbitrary unit length and a unit width perpendicular to the unit length in a relative moving direction to the laser beam, in the relative moving direction, with respect to the recording layer;

setting five stages or more irradiation times with respect to the virtual recording cell so that the irradiation time becomes long successively from the first to final stages;

setting a power average value of laser beam in a specific irradiation time of the plural-stage irradiation times so as to become larger than a power average value of another irradiation time longer than the specific irradiation time; and

5 forming recording marks being formed in the virtual recording cell and giving five stages or more different optical reflectance to the virtual recording cell when the laser beam is irradiated to the virtual recording cell.

10 (8) Further, the present invention provides the optical recording method, wherein in the plural irradiation times from the first stage to at least second stage, a power average value of laser beam of each stage is set so as to become longer than a power average value of another irradiation time longer than the plural irradiation times.

15 (9) Further, the present invention provides the optical recording method, wherein in at least first stage irradiation time, the power of laser beam is set larger than a reference power until the midway time point from the irradiation start time point, and is set to the reference power until the termination
20 time from the midway time point, and

in another irradiation time longer than the irradiation time, the power of laser beam is set to the reference power until the termination time from the irradiation start time point.

25 (10) Further, the present invention provides the optical recording method, wherein in at least first stage irradiation time, the power of laser beam is set larger than a reference power until the termination time point from the irradiation start

time point, and

in another irradiation time longer than the irradiation time, the power of laser beam is set to the reference power until the termination time from the irradiation start time point.

5 (11) Further, the present invention provides an optical recording method, which irradiates an laser beam to an optical recording medium including a reflective layer and a recording layer, and forms a recording mark is formed on the recording layer so as to record information, comprising the following stages of:

10 continuously forming a virtual recording cell, which has an arbitrary unit length and a unit width perpendicular to the unit length in a relative moving direction to the laser beam, in the relative moving direction, with respect to the recording layer,

15 setting five stages or more irradiation times with respect to the virtual recording cell so that the irradiation time becomes long successively from the first to final stages,

20 setting a reference time shorter than the final stage irradiation,

controlling the laser beam so that it is irradiated in all range at a power larger than a reference power in an irradiation time shorter than the reference time of the plural stage irradiation times, and is irradiated at a power larger than a reference power in an irradiation time longer than the reference time until the reference time elapsed from the irradiation start time point, and further, is irradiated at the reference power

after the reference time elapsed,

setting a power average value of the laser beam so as to become large in a manner that when the laser beam irradiation time is short, the irradiation time at the reference power after
5 the reference time elapsed decreases, and a ratio of the irradiation time at the larger power increases.

(12) Further, the present invention provides the optical recording method, wherein the recording layer contains an organic dye, and is applied in the case of recording information in the
10 recording layer.

In the above items (7) to (10), preferably, the laser beam is irradiated at a power larger than the reference power in each stage where the recording mark is formed so that a change of reflectance is less than 20% (0.2K) with respect to the optical
15 reflectance (initial reflectance) of the optical recording medium of no-recording state. Further, in the above items (1) or (7), the "specific irradiation time" means one or plural irradiation times selected from the plural stage irradiation times.

20

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a diagram to schematically explain a relation between a change of an irradiation time of laser beam and an optical reflectance of a virtual recording cell in the present
25 invention;

Fig. 2 is a perspective view partly in section showing principal parts of an optical recording medium to according to

a first embodiment of the present invention;

Fig. 3 is a block diagram showing an optical recording apparatus for recording information using a laser beam in order to record a data to the optical recording medium;

5 Fig. 4 is a schematic view showing a relation between a recording mark, the virtual recording cell and an optical reflectance in the case of forming the recording mark on a recording layer by the above optical recording apparatus;

10 Fig. 5 is a time chart showing a power stage state of laser beam irradiated to the optical recording medium according to the first embodiment of the present invention;

Fig. 6 is a diagram showing a state that an optical reflectance of the virtual recording cell is reduced by each recording mark in the optical recording medium;

15 Fig. 7 is a time chart showing a power stage state of laser beam irradiated to the optical recording medium according to a second embodiment of the present invention;

Fig. 8 is a time chart showing a power stage state of laser beam irradiated to the optical recording medium according to
20 a third embodiment of the present invention;

Fig. 9 is a time chart showing a power stage state of laser beam irradiated to the optical recording medium according to another example of the third embodiment of the present invention;
and

25 Fig. 10 is a schematically perspective view showing the case where the laser beam irradiated to the virtual recording cell has another shape.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

First, a description on the principle of the present invention is followed.

5 Fig. 1 shows a relation between a reduction state (shown by the solid line O) of optical reflectance of a recording mark and a time. In this case, the recording mark is formed in a virtual recording cell when a laser beam is irradiated to the virtual recording cell at a constant power over the maximum irradiation time T (maximum time usable for recording each virtual recording cell: this is called as allowable irradiation time).

10 As shown by the solid line O in Fig. 1, in the case where a laser beam is irradiated under the condition of constant power, an optical reflectance is not almost reduced in the initial time area A. Then, the optical reflectance is gradually reduced in an intermediate time area B, and further, its reduction speed increases as time elapses. In a termination time area C, the reduction speed gradually decreases.

15 The irradiation time of laser beam is preset at multiple stages, and then, the laser beam is irradiated to the virtual recording cell so as to form a recording mark (low optical reflectance area) having different size and giving different optical reflectance to the virtual recording cell; in this case, 20 the more the number of stages of the irradiation time is, the more a recording density can be improved. However, in the case where the maximum irradiation time (i.e., allowable irradiation

time) T usable for one virtual recording cell is constant, when the irradiation time is preset at multiple stages within a range of the allowable irradiation time, a "difference" between irradiation time becomes small. For this reason, it is difficult to accurately make the "difference" in the optical reflectance. If the difference of optical reflectance is too small, it is impossible to identify each recording mark (virtual recording cell) in reading.

Considering the above problem, in order to improve a read accuracy, the difference of optical reflectance must be securely made; therefore, it is desirable to obtain a large change of optical reflectance by a slight change of irradiation time. For example, in the solid line O, the actually usable area is an effective usable area U from the intermediate time area B to the termination time area C where the optical reflectance is securely reduced. Thus, the irradiation time is preset at multiple stages in an effective time stage range V corresponding to the above area U. This is a progressing technical concept of the present invention. In the intermediate time area B to the termination time area C, it is possible to obtain a relatively long effective time stage range V; therefore, five stages or more multi-level can be actually realized.

However, a time area from the initial time area A to the intermediate time area B (or, area where a change of optical reflectance is less than 20%) is not effectively utilized. In general, the time area is an area where it is impossible to sufficiently obtain a change of optical reflectance because a

reduction speed of optical reflectance is too slow, although it is different depending upon a kind of applied recording layer (kind of dye, etc.) and a shape of groove. As a result, the difference of optical reflectance is hard to be made in the case of achieving multi-level recording at further multiple stages; for this reason, there is some limitation in the time area.

9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214
2215
2216
2217
2218
2219
2220
2221
2222
2223
222

be achieved at multiple stages by both (U, V) of the solid line O and (U1, V1) of the solid line P. Further, the number of stages thus set is increased, and thereby, it is possible to further improve a recording density of optical recording medium.

5 By the way, the following case is considered; more specifically, in a state that the average value is intactly kept "large" in the solid line P, multi-level recording is realized in all stages of the irradiation time including the intermediate time area B and the termination time area C. However, in this case, as shown by a dotted line elongated from the solid line P, the reduction speed of optical reflectance becomes too fast by excessive power; for this reason, it is difficult to securely stage recording with a desired reflectance.

10 In other words, it is no significance to simply set the power average value larger in all stages. In short, the power average value is changed by the irradiation time, and thereby, multi-level recording is realized at multiple stages.

15 As seen from Fig. 1, the above average value is preferable in the following manner. More specifically, the average value is set to "large" in each recording mark having a change of reflectance less than 20% (0.2K) with respect to an optical reflectance K of no-recording state. On the other hand, the average value is set to "normal" (means that is smaller than "large") in each recording mark having a change of reflectance larger than 20%.

20 Next, the embodiments of the present invention will be detailedly described below with reference to Fig. 2 to Fig. 10.

In Fig. 2, there is shown an optical recording medium (disk) 10 to which the optical recording method according to the first embodiment of the present invention is applied. The optical recording medium 10 is a CD-R having a recording layer 12 using a dye, and is composed of a substrate 14 made of transparent base material, the above recording layer 12, a gold or silver reflection film (layer) 18, and a protective layer 20. More specifically, the recording layer 12 is formed out of dye applied so as to cover a laser beam guide groove 16 formed on one side (upper surface in Fig. 2) of the substrate 14. The reflection film 18 is formed on the upper side of the recording layer 12 by sputtering or the like, and the protective layer 20 is formed so as to cover the reflection layer 18.

The dye used for the recording layer 12 is an organic dye including cyanine, mero-cyanine, methine-based dye and its derivative, benzenethiol metal complex, phthalocyanine dye, naphthalocyanine dye, azo dye, etc.

The optical recording method of the present invention applied to the optical recording medium 10 is carried out by using an optical recording apparatus 30 as shown in Fig. 3.

The optical recording apparatus 30 is a CD-R recorder. The optical recording apparatus 30 rotates the optical recording medium (disk) 10 by a spindle motor 32 via a spindle servo 31 under the condition of constant linear velocity, and then, records information onto the optical recording medium (disk) 10 by a laser beam irradiated from a laser 36.

In the above laser 36, in accordance with information to

be recorded, a laser beam irradiation time to one of virtual recording cells (described later) 40 shown in Fig. 2 and Fig. 4, and an irradiation power are controlled by a laser driver 38. For example, the irradiation time is controlled by changing a laser pulse frequency. Further, the laser driver 38 has two power unit systems, and the first power unit and the second power unit are changed, and thereby, the irradiation power is set to two stages (high power S and reference power N).

10 In Fig. 3, a reference numeral 42 denotes a recording optical system including an objective lens 42A and a half-silvered mirror 42B. The objective lens 42A is controlled by a focus tracking servo 44 so that a laser beam is collected (focused) onto the recording layer 12 of the disk 10. Moreover, the objective lens 42A and the half silvered mirror 42B are controlled by a feed servo 46 so as to move at a predetermined speed from the inner peripheral side to the outer peripheral side of the disk 10 in synchronous with the rotation of the disk 10.

20 The above-mentioned spindle servo 31, laser driver 38, focus tracking servo 44 and feed servo 46 are controlled by a control unit 50. The data (information) to be recorded on the recording layer 12 is inputted to the control unit 50.

25 Subsequently, the following is a description on the virtual recording cell 40 and a recording mark recorded in the virtual recording cell 40.

As shown in Fig. 2, the virtual recording cell 40 is continuously formed along a rotational direction, that is, a

circumferential direction S of the disk 10 in the groove 16. As shown in Fig. 4, a length H in the circumferential direction of each virtual recording cell 40 is set shorter than a beam diameter (diameter of beam waist) D. Then, a laser beam is
 5 irradiated for each virtual recording cell 40, and thereby, recording marks 48A to 48G as schematically shown in Fig. 4 are formed in accordance with information to be recorded.

In this case, a size (magnitude) of the recording marks 48A to 48G expresses a degree of reduction of optical reflectance in each virtual recording cell 40 including recording mark. Namely, the larger the recording marks (low optical reflectance area) shown in Fig. 4 are formed, the lower the optical reflectance of the virtual recording cell 40 is. In fact, by a kind of dye used for the recording layer 12, the size or the size and optical
 10 transmittance of these recording marks 48A to 48G is variable in accordance with a laser beam irradiation time.

By doing so, for example, it is possible to form seven-stage recording marks 48A to 48G (the reduction of optical reflectance in the virtual recording cell 40 is expressed by each size of
 15 the recording marks) as shown in Fig. 4. Further, in the case where a read laser beam is irradiated to the recording marks 48A to 48G, an optical reflectance of reflected light has in the virtual recording cell 40 seven stages.

In this case, the optical transmittance of the recording
 20 marks 48A to 48G changes. This has the same meaning such that the optical transmittance and/or refractive index of the recording layer 12 in the recording marks 48A to 48G changes.

Thus, the following presumption is made. More specifically, the material forming the recording layer 12 is decomposed and modified in its quality by the laser beam irradiation, and then, the modified degree (what is called, burned degree) is different in each of the recording marks 48A to 48G. Therefore, the optical reflectance changes, and the modified portion (what is called, burned portion) is different in the thickness direction, and thereby, the optical reflectance changes.

Next, the following is a description on an optical recording method.

As already described in the optical recording medium 10, plural virtual recording cells 40 are continuously provided along the relative moving direction S so as to have an arbitrary unit length H along the relative moving direction to the laser beam and a unit width W perpendicular to the length H. In this embodiment, the optical recording medium 10 is rotating at a predetermined speed (in this case, 4.8 m/s); therefore, a continuous predetermined time (in this case, 125 ns) is arbitrarily preset in the optical recording apparatus 30, and thereby, the unit length H ($0.6\mu\text{m} = 4.8 \text{ m/s} \times 125 \text{ ns}$) of the virtual recording cell 40 is determined.

Incidentally, the unit width W of the virtual recording cell 40 is determined as the width of the groove 16; in this case, the width other than above may be determined.

Moreover, as shown in Fig. 5, five stages or more irradiation times (seven stages in this embodiment) are preset with respect to the virtual recording cell 40. In this case,

the stage of irradiation time includes the first stage to the final stage, which successively become long.

In this case, in the irradiation times T1, T2 and T3 from the first to third stages (although there is no problem in the first stage at least), the laser beam is set to a high power S larger than the reference power N until the midway time points Y1, Y2 and Y3 from the irradiation start. Thereafter, the laser beam is set to the reference power N until the termination time from the midway time points Y1, Y2 and Y3. Therefore, for example, an average value Pw of power irradiated in the first stage is obtained from the following equation $\{S \times Y1 + N \times (T1 - Y1)\} / T1$. Further, the second and third stage irradiation times are obtained in the same manner as above. In this case, the midway time points Y1 to Y3 are different in each stage; however, of course, the first to third stage the midway time points may be set to the same time point.

In the fourth to seventh stages irradiation times T4 to T7 longer than the third stage irradiation time T3, the laser beam is set to the reference power N from the irradiation start time to the termination time. Therefore, each average value Pw of power irradiated in the fourth to seventh stages is all reference power N.

As a result, the power average value Pw of laser beam in a specific irradiation time (any) of seven stage irradiation times is set so as to become larger than the average value Pw (N) in another irradiation time longer than the specific irradiation time. In this case, as the specific irradiation

time, one may be arbitrarily selected from the first to third stage irradiation times; on the other hand, as another irradiation time, any of the fourth to seventh stage irradiation times T4 to T7 may be selected.

5 Likewise, the plurality of irradiation times T1 to T3 from the first to third stages is considered as a set. Thus, in the plurality of irradiation times T1 to T3, a power average value P_w of laser beam in each stage is set so as to become larger than a power average value $P_w(N)$ in another irradiation time longer than these irradiation times. In this case, as another irradiation time, one may be arbitrarily selected from the fourth to seventh stage irradiation times T4 to T7.

10 Under the power condition shown in Fig. 5, a laser beam is irradiated to the virtual recording cell 40, and thereby, the virtual recording cell 40 is formed with recording marks 48A to 48G having seven stage different optical reflectance.

15 Fig. 6 shows a relation between seven stage irradiation times T1 to T7 and a reduction of optical reflectance of the virtual recording cell 40 by the recording marks 48A to 48G formed by these irradiation times in this recording method.

20 In the first to third stage irradiation times T1 to T3, their power average values of laser beam are larger than those after the fourth stage irradiation time; therefore, the optical reflectance is reduced soon, and a desired reduction is obtained for a short time. On the other hand, in the fourth to seventh stage irradiation times T4 to T7, write is carried out in an area where a reduction speed of optical reflectance is properly

stable.

As described above, in the optical recording medium and method according to the first embodiment, the power average value of laser beam is properly controlled by the irradiation time. Therefore, the recording marks 48a to 48C can be formed at multiple stages in a short irradiation time area (first to third stage irradiation times in this embodiment) where it has been considered to be impossible in a process of development). As a result, it is possible to further increase the number of stages, and to improve a recording density. Further, in the case where the irradiation time is long, the power average value is set smaller than the case where the irradiation time is short; therefore, it is possible to keep a state that the optical reflectance of the virtual recording cell is properly reduced for a long time. As a result, the recording marks 48D to 48G can be securely formed over the multiple stages from the fourth to the seventh stages.

By the way, the recording power is set to two stages so as to become a high power S in irradiation start in the first to third stages. It is not a principal object to sharpen a mark edge of the recording mark. Because, according to the optical recording method, the recording mark is securely recorded in the virtual recording cell, and then, the number of stages is recognized by a change of optical reflectance of the virtual recording cell, and thus, multi-level recording can be achieved.

More specifically, like the conventional binary recording, in a situation such that a "length" of the recording mark must

be recognized, there is a need of securely judge the start time point of the recording mark. In the light of the above situation, the rise (mark edge) of the recording mark must be sharpened; for this reason, the power of laser beam has been controlled so as to become large to some degree. However, in this embodiment, 5 in order to realize further multiple stage recording, the power of laser beam is changed over as a principal object for controlling a change speed of optical reflectance.

10 In this embodiment, the power of laser beam is changed into two stages (reference power N and high power S), and thereby, the power average value has been changed. Under the same concept as above, the power of laser beam is changed into three stages or more, and thereby, the power average value may be changed. Further, the power average value has been set to "large" from 15 the first to third stages, and is set to "normal" from the fourth to seventh stages. The present invention is not limited to the above embodiment, and the difference is made in a manner that in arbitrarily selected two different irradiation times, a shorter irradiation time has the "large" average value; on the 20 other hand, a longer irradiation time has the "normal" average value. Therefore, so long as the above difference is made, the technical concept belongs to the scope of the present invention (even if the above situation is not established in the case of selecting two other irradiation times).

25 Next, the following is a description on optical recording medium and method according to the second embodiment of the present invention. In this case, the optical recording medium

and apparatus has the same basic structure as the optical recording medium 10 and the optical recording apparatus 30 described in the above first embodiment. Therefore, like reference numerals are used to designate the same components and members, and the explanation and illustration of these components or the like are omitted.

In the optical recording medium 10 and the optical recording method of this second embodiment, the virtual recording cell 40 is continuously provided along the relative moving direction S so as to have an arbitrary unit length H along the relative moving direction to the laser beam and a unit width W perpendicular to the length H. In this case, in the same manner as the above first embodiment, the optical recording medium 10 is rotating at a predetermined speed (in this case, 4.8 m/s). Therefore, a continuous predetermined time (in this case, 125 ns) is arbitrarily preset in the optical recording apparatus 30, and thereby, the unit length H ($0.6 \mu\text{m} = 4.8 \text{ m/s} \times 125 \text{ ns}$) of the virtual recording cell 40 is determined.

Moreover, as shown in Fig. 7, five (5) stages or more irradiation times (seven stages in this embodiment) are preset with respect to the virtual recording cell 40. In this case, the stage of irradiation time includes the first stage to the final stage, which successively become long.

In this case, in the irradiation times T1, T2 and T3 from the first to third stages (although there is no problem in the first stage at least), the laser beam is set to a high power S larger than the reference power N until the termination time

point from the irradiation start point.

Further, in the fourth to seventh stage irradiation times T4 to T7 longer than the third stage irradiation time T3, the laser beam is set to the reference power N from the irradiation start time to the termination time. Therefore, each average value P_w of power irradiated in the first to third stages is all high power S; on the other hand, each average value P_w of power irradiated in the fourth to seventh stages is all reference power N.

10 As a result, the power average value P_w (S) of laser beam in a specific irradiation time (any) of seven stage irradiation times is set so as to become larger than the average value P_w (N) in another irradiation time longer than the specific irradiation time. In this case, the specific irradiation time
15 corresponds to any of the first to third stage irradiation times; on the other hand, another irradiation time may be any of the fourth to seventh stage irradiation times T4 to T7.

Likewise, the plurality of irradiation times T1 to T3 from the first to third stages (by at least second stages in the present invention) is considered as a set. Thus, in the plurality of
20 irradiation times T1 to T3, a power average value P_w (S) of laser beam in each stage is set so as to become larger than a power average value P_w (N) in another irradiation time longer than these irradiation times. In this case, as another irradiation
25 time, any of the fourth to seventh stage irradiation times T4 to T7 may be arbitrarily selected.

Under the power condition shown in Fig. 7, a laser beam

is irradiated to the virtual recording cell 40, and thereby, the virtual recording cell 40 is formed with recording marks 48A to 48G which bring seven stage different optical reflectance to the virtual recording cell 40.

5 In this second embodiment, it is possible to obtain the quite same effect as the above first embodiment. Further, like the first embodiment, there is no need of carrying out a control for changing the power of laser beam using the midway time points Y1, Y2 and Y3; therefore, it is possible to readily realize multi-level recording. In this case, the power of laser beam may be changed into three stages; for example, the power of laser beam may be set so as to successively becomes weak in the first to seventh stages.

10 Next, the following is a description on optical recording medium and method according to the third embodiment of the present invention. In this case, the optical recording medium and apparatus has the same basic structure as the optical recording medium 10 and the optical recording apparatus 30 described in the above first embodiment. Therefore, like reference numerals are used to designate the same components and members, and the explanation and illustration of these components or the like are omitted.

15 In the optical recording medium 10 and the optical recording method of this third embodiment, plural virtual recording cells 40 are continuously provided along the relative moving direction S so as to have an arbitrary unit length H along the relative moving direction to the laser beam and a unit width

W perpendicular to the length H.

Moreover, as shown in Fig. 8, five stages or more irradiation times (seven stages in this embodiment) are preset with respect to the virtual recording cell 40. In this case, 5 the stage of irradiation time includes the first stage to the final stage, which successively become long.

Further, a reference time L is set so as to become shorter than the seventh stage irradiation time T7, which is the final stage. More specifically, in this third embodiment, the 10 reference time L is set so as to become longer than the third stage irradiation time T3 and to become shorter than the fourth stage irradiation time T4.

Of all stage irradiation times T1 to T7, in the irradiation times (T1 to T3 in this case) shorter than the reference time 15 L, the laser beam is irradiated over all range at the high power S larger than the reference power N. On the other hand, in the irradiation times (T4 to T7 in this case) longer than the reference time L, the laser beam is irradiated at the high power S (larger than the reference power N) until the reference time L elapsed 20 from the irradiation start time point. Then, after the reference time L elapsed, the laser beam is irradiated at the reference power. Namely, the time until the reference time L elapsed from the irradiation start is determined as a strong irradiation interval E, on the other hand, the time after the reference time 25 L elapsed is determined as a normal irradiation interval F.

By doing so, when the irradiation times T1 to T7 of laser beam are short, the irradiation time at the reference power N

(i.e., irradiation time in the normal irradiation interval F) after the reference time L elapsed decreases. On the other hand, the irradiation time (i.e., irradiation time in the strong irradiation interval E) at the high power S increases. As a result, the shorter the irradiation times T1 to T7 are, the larger the power average value of laser beam becomes.

For example, a power average value Pw7 in the seventh stage irradiation is obtained from the following equation.

$$Pw7 = \{S \times L + N \times (T7 - L)\} / T7$$

Further, a power average value Pw4 in the fourth stage irradiation is obtained from the following equation.

$$Pw4 = \{S \times L + N \times (T4 - L)\} / T4$$

In this case, in the above equations, L is constant, and the relations of $S > N$ and $T4 < T7$ are formed; therefore, the relation of $Pw4 > Pw7$ is formed. Thus, it can be seen that when the irradiation time is short, the average value becomes large. In the first to third stages, the irradiation time of the normal irradiation interval F becomes zero, and the power average value is S.

In an optical recording medium 10 of the third embodiment and the recording method, the same effect as the above first and second embodiments can be obtained. The power is set to two stages (S, N); nevertheless, it is possible to stepwise change the power average value by a ratio of irradiation time.

Incidentally, the reference time L is set between the third stage irradiation time T3 and the fourth stage irradiation time T4. In this case, the reference time L may be set anywhere so long

as it is set within a range of the maximum irradiation time. For example, as shown in Fig. 9, the reference time L may be set to a time shorter than the first stage irradiation time T1.

As described in the first to third embodiments, the optical recording medium and the optical recording method are adaptable to the case where the recording layer 12 of the optical recording medium 10 contains an organic dye component. In this case, of course, the present invention may be applicable to other recording layers containing no organic dye component, for example, recording layers formed of inorganic dye and other materials.

The above embodiments have described the case where the above optical recording medium 10 is a CD-R disk. The optical recording medium of the present invention is not limited to the above CD-R disk, and is widely applicable to other optical recording medium. In addition, the optical recording medium of the present invention is not limited to the disk-like rotating element.

Further, the size of the virtual recording cell 40 set when forming the recording mark by the optical recording apparatus 30 is not limited to the above embodiment. In particular, it is preferable that the length of the virtual recording cell 40 is set so as to become equal to the width of the groove 16 so long as the beam waist diameter of laser beam is further made small. On the other hand, in the case of recording the recording mark at multiple stages such as five stages, the length of the virtual recording cell 40 may be set larger than the laser beam waist. In this case, part of the recording marks

can be made into a size more than the beam waist.

Moreover, the recording laser beam has a circular shape in the recording layer 12. As shown in Fig. 10, however, this can utilize, for example, a beam shaping prism 42C in addition to the objective lens 42A and the beam shape may be formed into an elliptic or linear shape as shown in Fig. 10, which is short in the feed direction of the optical recording medium 10, and is long in the direction perpendicular to the feed direction. In this case, a recording mark 49 becomes short, so that the virtual recording cell can be further shortened. In other words, it is possible to improve a recording density.

Further, the optical recording medium of this embodiment may be constructed so as to previously have a plurality of pits as shown by a reference numeral 52 in Fig. 2, which have the number of different reflectance corresponding to the signal modulation stages of the optical recording medium 10. The following specific information may be recorded in the plurality of pits 52. More specifically, the information includes information for individually identifying the optical recording medium 10, information for identifying whether a recording medium is an optical recording medium for multi-level recording, power information of laser beam for recording and reading the recording medium, etc. The following case is a concept included in the scope of the present invention. Namely, specific information is read in the optical recording medium 10 in recording, and then, according to the recorded information, the reference power is set so as to achieve optical recording.

Besides, by the above specific information, it is possible to securely identify whether a recording medium is an optical recording medium for multi-level recording, and to determine an irradiation time of laser beam in accordance with the number of stages of pit previously recorded. Therefore, multi-level recording and reading can be further securely carried out.

As shown by a reference numeral 56 in Fig. 2, the laser beam guide groove is provided with a groove partition, which partially partitions the groove, and thereby, the same effect as above can be obtained. The groove partition may be usable solely or may be combined.

As is evident from the above description, according to the present invention, it is possible to provide an optical recording medium having recording marks formed at multiple stages, and to greatly improve an information recording density.